

Werkstoffbezeichnungen nach ASTM-D 1418-76

De Beer Group

www.jdebeer.nl

www.koero.de



	Polymer	div. Handelsnamen
NR IR	Naturkautschuk Isoprenkautschuk	Natsyn, Cariflex IR
SBR BR	Styrol-Butadien-Kautschuk Butadien-Kautschuk	Buna Hüls, Polysar S, Solprene Buna CB, Polybutadien K
IIR	Butyl-Kautschuk	Polysar Butyl, Esso-Butyl
EPDM	Äthylen-Propylen- Terpolymerisat	Keltan, Buna AP, Dutral
NBR	Acrylnitril-Butadien- Kautschuk	Perbunan, Polysar- Krynak, Nycar, Chemigum
ECO	Epichlorhydrin-Kautschuk	Herclor, Hydrin
CR	Chloropren-Kautschuk	Baypren, Neoprene
CSM	Chlorsulfonisiertes Polyäthylen	Hypalon, Noralon
AU, EU	Urethan-Kautschuk	Urepan, Adiprene C
T	Polysulfid-Kautschuk	Thiokol
Q, SI	Silicon-Kautschuk	Silopren
FQ, FSI	Fluor-Silicon-Kautschuk	Silastic
FKM	Fluorkautschuk	Fluorel, Viton, Tecnoflon
ACM	Polyacrylat-Kautschuk	Hycar